

TECHNICAL DATASHEET

Printing date: 21/03/2017

Revision date: 25/01/2017

SECTION 1.- DESCRIPTION

Matte acrylic paint based on acrylic resins in a watery dispersion and highly resistant light-fastness pigments. Ideal for decoration and protection of interior and exterior surfaces.

SECTION 2.- CHARACTERISTICS

- High covering power.
- Excellent adhesion on cement, concrete, brick and other construction materials.
- Stable white, not yellow.
- Forms a highly mould-resistant film.
- Well-balanced whiteness, for protection of indoor walls.
- Complete impermeability to rain and U.V. light.
- Not self-ignitable
- Fireproof
- Breathable

SECTION 3.- TECHNICAL SPECIFICATIONS

Colour	White
Aspect	Liquid
Film aspect	Matte
Odour	Characteristic
Solvent	Water
Density	1.66 gr/cm ³ aprox.
Drying time (minimum)	30 minutes
Coverage	9-13 m ² /L. according to surface conditions and absorption
Second coat waiting time (minimum)	2 – 4 hours (20° C and 65% relative humidity)
Viscosity	67% ±2% weight
Washability	High
Resistance to wet scrub	Above 4.500 cycles (UNE 48243)
Cleaning tools	Water

SECTION 4.- ATTRIBUTES

This paint has a well-balanced whiteness, and is easy to use. High washability and high covering power for interior and exterior surfaces.



PIMACRIL

SECTION 5.- APPLICATION

Suitable for decoration and protection of interior and exterior surfaces such as concrete, gypsum, plaster and heat-resistant materials.

SECTION 6.- ADVICE

Available to use with brush, roller or spray gun. The surfaces must be prepared, firm, dry and cleaned in order to get free of dust, dirt, oil, grease, wax, chalk. All surfaces with old paintings must be scraped and fully cleaned. When old paints are well fixed and it is not possible to scrap, apply a coat of fixer. Do not apply under 5° C.

SECTION 7.- SIZES

Containers available for 4 L and 15 L.

SECTION 8.- STORAGE

Original, unopened containers may be stored up to 12 months. Preserve from direct sun exposure as well as from freezing.

SECTION 9.- REMARKS

The information in this Technical Datasheet is the result of Pimasa's knowledge, based on laboratory testing and practical experience. Pinturas Pimasa reserves the right to modify the data provided without prior notice. If there is any inconsistency between different language issues in this document, the Spanish version shall prevail.