

# Pimasa



**POOLS**

## TECHNICAL DATASHEET

Printing date: 05/05/2020

Revision date: 30/03/2017

### SECTION 1.- DESCRIPTION

Matte acrylic paint based on acrylic resins in a watery dispersion and highly resistant light-fastness pigments. Ideal for painting pools.

### SECTION 2.- CHARACTERISTICS

- Excellent adhesion on cement, concrete, brick and other construction materials.
- Completely waterproof.
- Non combustible
- Breathable

### SECTION 3.- TECHNICAL SPECIFICATIONS

<b>Colour</b>	Blue
<b>Aspect</b>	Liquid
<b>Film aspect</b>	Matte
<b>Odour</b>	Characteristic
<b>Solvent</b>	Water
<b>Density</b>	1.35 gr/cm <sup>3</sup> ± 0.005 kg/l according ISO 1675
<b>Drying time (minimum)</b>	30 minutes
<b>Coverage</b>	6-8 m <sup>2</sup> /L. according to surface conditions and absorption
<b>Second coat waiting time (minimum)</b>	2 – 4 hours (20º C and 65% relative humidity)
<b>Cleaning tolos</b>	Water

### SECTION 4.- ATTRIBUTES

This paint has an excellent adhesion on cement and concrete. It is breathable and completely waterproof with a completely resistance to pool purification agents. Alkali-resistant for brackets and fast drying with bactericide and algaecide action.

### SECTION 5.- APPLICATION

Homogenize the product before use.

The Technical Data Sheet (TDS) is recommended to be read in conjunction with the Safety Data Sheet (SDS) for this product.  
[www.pinturaspimasa.com](http://www.pinturaspimasa.com)

# Pimasa



## POOLS

**Preliminaries:** The surfaces must be prepared, dry and cleaned in order to get free of salt, dirt, oil, grease, chalk...

**New pools:** Keep plenty of water during 30-45 days in process to dissolve salt contained. Then, clean with hydrochloric acid to 10%-15% dissolution and leave during 5 minutes. Rinse with enough water and wait to dry. Apply the first coating with 10%-15% water dissolution. For the second coating apply one or two coats without dissolution.

**Unpainted old pools:** All surfaces with old paintings must be scraped and fully cleaned to eliminate mould and any dirt. Then, rinse with enough water and paint as a new pool.

**Pools to repaint:** if old paint is in good condition cleans dirt and apply one or two coats. If paint is in no good conditions, the coat must be removed and apply a first coat with 10% dissolution and second coating apply one or two coats without dissolution.

### SECTION 6.- ADVICE

Available to use with brush or roller.

### SECTION 7.- SIZES

Containers available for 4 L and 15 L.

### SECTION 8.- STORAGE

Original, unopened containers may be stored up to 12 months. Preserve from direct sun exposure as well as from freezing.

### SECTION 9.- REMARKS

The information in this Technical Datasheet is the result of Pimasa's knowledge, based on laboratory testing and practical experience. Pinturas Pimasa reserves the right to modify the data provided without prior notice. If there is any inconsistency between different language issues in this document, the Spanish version shall prevail.